

Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) **EP 0 774 883 A2**

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:
21.05.1997 Bulletin 1997/21

(51) Int. Cl.⁶: **H05B 33/14**, **H05B 33/12**

(21) Application number: 96118022.1

(22) Date of filing: 11.11.1996

(84) Designated Contracting States:
DE FR GB

(30) Priority: 17.11.1995 US 560453

(71) Applicant: **MOTOROLA, INC.**
Schaumburg, IL 60196 (US)


(72) Inventors:
• **Shi, Song Q.**
Phoenix, Arizona 85044 (US)

• **Gorsuch, Cynthia A.**
Glendale, Arizona 85308 (US)

(74) Representative: **Hudson, Peter David et al**
Motorola,
European Intellectual Property Operations,
Midpoint
Alencon Link
Basingstoke, Hampshire RG21 7PL (GB)

(54) Organic electroluminescence device with mixed hole transporting materials

(57) An organic electroluminescent device (10) is disclosed which has a cathode (16), an electron transporting zone (15), an emitting zone (14), an hole transporting zone (13) and an anode (12) that are laminated in sequence. The hole transporting zone (13) includes at least one hole transporting layer fabricated with two or more homogeneously mixed hole transporting materials each having a glass transition temperature above 75 °C and which are structurally compatible.



↑
10

EP 0 774 883 A2

Description

Field of the Invention

5 This invention relates to an organic electroluminescence (EL) device, and more particularly to an organic EL device where two or more mixed hole transporting materials are used in a hole transporting layer.

Background of the Invention

10 Organic electroluminescent (EL) devices are generally composed of three zones of organic molecules sandwiched between transparent and metallic electrodes, the three zones include an electron transporting zone, an emissive zone and a hole transporting zone. Organic EL devices are attractive, owing chiefly to low driving voltage, with a potential application to full color flat emissive displays. Though significant lifetime has been achieved in the prior art (See US Patent No. 4,720,432, entitled "Electroluminescent device with Organic Luminescent Medium", issued January 19, 1988),
15 further improvement is needed for applications where high brightness is required. In general, the hole transporting materials used in the hole transporting zone of an organic EL device are the most vulnerable parts which are susceptible to thermal degradation by physical aggregation or recrystallization.

To address the thermal degradation problem of the hole transporting materials in an organic EL device, several schemes have been proposed: one being a double-layer hole transporting configuration (see US Patent 5,256,945, entitled "Organic Electroluminescence Element", issued October 26, 1993); one being usage of materials of high glass transition temperatures (see US Patent 5,061,569, entitled "Electroluminescent Device with Organic Electroluminescent Medium", issued October 29, 1991).
20

It is a purpose of this invention to provide a new device and method to reduce the thermal degradation of the hole transporting materials in the hole transporting zone of an organic EL device. As a result, the durability of an organic EL device is significantly improved.
25

Summary of the Invention

30 To at least partially solve the above problems and others and to realize the above purpose a new and improved organic EL device is provided which includes a cathode, an electron transporting zone, an emitting zone, an hole transporting zone and an anode that are laminated in sequence. The hole transporting zone is made of one or two hole transporting layers, wherein at least one hole transporting layer is comprised of two or more homogeneously mixed hole transporting materials which are structurally compatible.

According to the present invention, there is obtained an organic EL device with an improved lifetime by suppression of the aggregation or recrystallization tendency of hole transporting materials.
35

Brief Description of the Drawing

40 The single figure is a simplified sectional view of a light emitting diode in accordance with the present invention.

Description of the Preferred Embodiments

The present invention is directed to a new scheme for use in organic light emitting devices which, in general, consist of thin layers of organic molecules sandwiched between transparent and metallic electrodes.

45 The single Figure illustrates in a simplified cross-sectional view, one embodiment of an organic light emitting device (LED) 10. Organic LED 10 includes a transparent substrate 11 which in this specific embodiment is a glass or plastic plate having a relatively planar upper surface. A transparent electrically conductive layer 12 is deposited on the planar surface of substrate 11 so as to form a relatively uniform electrical contact. An hole transporting zone 13 made of organic hole transporting materials is deposited on the surface of conductive layer 12. A light emission zone 14 made of a host emissive material containing a guest fluorescent dopant is deposited onto the surface of hole transporting zone 13. Then an electron transporting zone 15 made of an electron transporting material is deposited on the surface of light emission zone 14 and a second electrically conductive layer 16 is deposited on the upper surface of electron transporting zone 15 to form a second electrical contact.
50


In this embodiment, conductive layer 16 is formed of any of a wide range of metals or alloys in which at least one metal has a work function less than 4.0 eV. By the proper selection of material for conductive layer 16, the work functions of the materials making up layers 15 and 16 are substantially matched to reduce the required operating voltage and improve the efficiency of organic LED 10. Additional information on work function matching is disclosed in a copending U.S. Patent Application entitled "Organic LED with Improved Efficiency", filed 12 September 1994, bearing serial number 08/304,454, and assigned to the same assignee.
55

In this embodiment conductive layer 12 is a p-type contact and conductive layer 16 is an n-type contact. A negative terminal of a potential source 17 is connected to conductive layer 16 and a positive terminal is connected to conductive layer 12. When a potential is applied between layers 12 and 16 by means of potential source 17, electrons injected from the n-type contact (layer 16) are transported through organic layer 15 and into organic layer 14 (the emissive layer) and holes injected from the p-type contact (layer 12) are transported through organic layer 13 and into organic layer 14 (the emissive layer), where upon an electron and a hole recombination a photon is emitted.


It has been recognized that the hole transporting materials made up of tertiary aromatic amines are the least thermally stable materials in organic electroluminescent devices. Especially, when an organic EL device is driven at high electric current density, the hole transporting materials in the hole transporting zone tend to aggregate or reorganize to form islands, domains and pinholes. The change in film uniformity and homogeneity of the hole transporting materials initially causes a graduated degradation in device luminance and eventually the device failure.

Generally, the glass transition temperature (T_g) of a material is an indicator for thermal stability of the resulting amorphous films. A higher glass transition temperature offers higher thermal stability for an amorphous film. A large molecular weight and strong steric hindrance to stacking are two of the main factors that determine the glass transition temperature of an organic material.


In an effort to improve the reliability of organic EL materials, Shirota (see J. Phys. Chem. 1993, 97, 6240 and reference within) and Adachi (Appl. Phys. Lett, 1995, 66 (20), 2679) have designed and prepared several symmetric globular tertiary aromatic amines with high T_g , yielding homogeneous amorphous films for organic EL applications. In the prior art, the following compounds represented by HTM-1, HTM-2 and HTM-3 and HTM-4 are a few organic hole transporting materials with T_g above 75 °C, which give improved lifetimes when used in organic EL devices.




HTM-1



HTM-2



HTM-3




HTM-4


Since at present almost all reliable organic EL devices are fabricated with evaporative technology, improving device reliability by increasing T_g of hole transporting materials has some limits. When T_g reaches a certain point, the molecular weight of an organic molecule may be so large that it is no longer sublimable or evaporatable.

According to the present invention, organic EL device 10 as illustrated in the figure includes hole transporting zone 13 made of one or two hole transporting layers, wherein at least one of the hole transporting layers includes two or more homogeneously mixed hole transporting materials that are structurally compatible. It is desirable that each of the individual hole transporting materials used in hole transporting zone 13 in organic EL device 10 has a glass transition temperature, before mixing, above 75 °C. However, it is preferred that hole transporting materials having a glass transition temperature greater than 90 °C are used to achieve a longer lasting organic EL device 10.


It should be emphasized that the hole transporting materials with T_g below 75 °C may not give a very stable device even when used as a mixture. For instance, an organic EL device fabricated with TPD, having a T_g of 63 °C, as hole transporting material only has a lifetime of a few hours, while fabricating the same device with TPDs (illustrated below) containing a mixture of TPD (86.5%), TPD-1 (13.1%), TPD-2 (0.4%) as hole transporting material has a somewhat better, yet still short, lifetime of a couple dozen hours. The mixture of TPD with its two derivatives has less tendency to crystallize than anyone of the materials alone, thus making the mixture more desirable but still not as stable as required for longer lasting organic EL devices.



TPD




TPD-1




TPD-2

45 Hole transporting materials used in accordance with the present invention include organic tertiary aromatic amines with T_g greater than 75 °C. The aromatic amines have a general structure of




55 where: Ar₁, Ar₂ and Ar₃ are independently aromatic hydrocarbons or aromatic tertiary amine moieties. The aromatic hydrocarbons and the aromatic tertiary amine moieties in turn can be substituted. Typical substituents include alkyl groups, alkoxy groups, alkylamine groups, aryl groups, aryloxy groups, arylamine groups and halogen such as bromide, chloride, and fluoride.


The following is an exemplary list of a few classes of aromatic tertiary amines satisfying the requirement of the present invention:




Class-1




Class-2



Class-3




Class-4




Class-5

Where R₁, R₂, R₃, R₄ and R₅ are independently selected from alkyl groups, alkoxy groups, alkylamine groups, aryl groups, aryloxy groups, arylamine groups and halogen such as bromide, chloride, and fluoride; each of R₁, R₂, R₃, R₄ and R₅ may also be an independently fused aromatic ring.

In this specific embodiment, the two or more hole transporting materials mixed in one layer of hole transporting zone 13 of organic EL device 10 can be from any of the different classes, such as Class-1, Class-2, Class-3, Class-4, Class-5, mentioned above as long as a homogeneous, uniform and stable amorphous film is obtained. However, it is preferred that materials from the same class with similar structures but different substituents on their backbone structures, namely, homologues, are mixed in a layer of hole transporting zone 13 of organic EL device 10 to achieve the best results. For example, HTM-1 (described above) from Class-3 can be mixed with the following two hole transporting materials (HTM-5 and HTM-6) also from Class-3 in any pre-determined ratio:




HTM-5




HTM-6

The mixing of two hole transporting materials in one layer of hole transporting zone 13 can be achieved by several methods including pre-mixing and co-evaporation. The pre-mixing method involves physically mixing two or more hole transporting materials in a pre-determined ratio to a homogeneous state before the mixture is loaded into an evaporation boat for device fabrication. The pre-mixing method is used when all hole transporting materials to be mixed have a similar sublimation temperature. The co-evaporation method involves evaporating different hole transporting materials from different evaporation boats simultaneously. The mixing ratio is determined by the relative evaporation rate of each material. The co-evaporation method is used when the hole transporting materials to be mixed have substantial differences in sublimation temperature. The pre-mixing method is generally preferred for its simple, more cost-effective process as compared to the co-evaporation method.


Although, at the present time the most reliable organic EL devices are fabricated mainly with the previously discussed aromatic tertiary amines as a hole transporting material, other organic hole transporting materials such as aromatic silanes, aromatic silazanes and aromatic phosphine can also be used in the present invention as long as those materials have a T_g greater than 75 °C:



Silanes



Silazanes




Phosphines

where: Ar₁, Ar₂ and Ar₃ are independently aromatic hydrocarbons or aromatic tertiary amine moieties. The aromatic hydrocarbons and the aromatic tertiary amine moieties in turn can be substituted. Typical substituents includes alkyl groups, alkoxy groups, alkylamine groups, aryl groups, aryloxy groups, arylamine groups and halogen such as bromide, chloride, and fluoride.

While we have shown and described specific embodiments of the present invention, further modifications and improvements will occur to those skilled in the art. I desire it to be understood, therefore, that this invention is not limited to the particular forms shown and I intend in the appended claims to cover all modifications that do not depart from the spirit and scope of this invention.


Claims

1. An organic electroluminescence device (10) with a cathode (16), an electron transporting zone (15), an emitting zone (14), an hole transporting zone (13) and an anode (12) which are laminated in sequence, wherein said hole transporting zone (13) includes at least one hole transporting layer comprising a plurality of homogeneously mixed hole transporting materials each having a glass transition temperature above 75 °C.
2. An organic electroluminescence device as claimed in claim 1, wherein the hole transporting materials are structurally compatible so as to form a stable, homogeneous, uniform film.
3. An organic electroluminescence device as claimed in claim 1, wherein the hole transporting materials are selected from organic tertiary aromatic amines having a general structure of




where: Ar₁, Ar₂ and Ar₃ are independently aromatic hydrocarbons, or aromatic tertiary amine moieties, and wherein the aromatic hydrocarbons and the aromatic tertiary amine moieties in turn can be substituted with substituents selected from alkyl groups, alkoxy groups, alkylamine groups, aryl groups, aryloxy groups, arylamine groups and halogen such as bromide, chloride, and fluoride.


4. An organic electroluminescence device as claimed in claim 3, wherein the hole transporting materials are selected from organic tertiary aromatic amines having at least one of the following chemical formulas:




Class-1




Class-2



Class-3




Class-4




Class-5

where R_1 , R_2 , R_3 , R_4 and R_5 are independently selected from alkyl groups, alkoxy groups, alkylamine groups, aryl groups, aryloxy groups, arylamine groups and halogen such as bromide, chloride, fluoride and a fused aromatic ring.


5. An organic electroluminescence device as claimed in claim 1, wherein the hole transporting materials are selected from organic aromatic silanes, aromatic silazanes and aromatic phosphine with general formulas:



Silanes




Silazanes




Phosphines

where: Ar₁, Ar₂ and Ar₃ are independently aromatic hydrocarbons, or aromatic tertiary amine moieties, and wherein the aromatic hydrocarbons and the aromatic tertiary amine moieties in turn can be substituted with substituents selected from alkyl groups, alkoxy groups, alkylamine groups, aryl groups, aryloxy groups, arylamine groups and halogen such as bromide, chloride, and fluoride.



↑
10

THIS PAGE BLANK (USPTO)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) **EP 0 774 883 A3**

(12)

EUROPEAN PATENT APPLICATION

(88) Date of publication A3:
30.07.1997 Bulletin 1997/31

(51) Int. Cl.⁶: **H05B 33/14**, H05B 33/12

(43) Date of publication A2:
21.05.1997 Bulletin 1997/21

(21) Application number: 96118022.1

(22) Date of filing: 11.11.1996

(84) Designated Contracting States:
DE FR GB

(30) Priority: 17.11.1995 US 560453

(71) Applicant: **MOTOROLA, INC.**
Schaumburg, IL 60196 (US)


(72) Inventors:
• Shi, Song Q.
Phoenix, Arizona 85044 (US)

• Gorsuch, Cynthia A.
Glendale, Arizona 85308 (US)

(74) Representative: Hudson, Peter David et al
Motorola,
European Intellectual Property Operations,
Midpoint
Alencon Link
Basingstoke, Hampshire RG21 7PL (GB)

(54) Organic electroluminescence device with mixed hole transporting materials

(57) An organic electroluminescent device (10) is disclosed which has a cathode (16), an electron transporting zone (15), an emitting zone (14), an hole transporting zone (13) and an anode (12) that are laminated in sequence. The hole transporting zone (13) includes at least one hole transporting layer fabricated with two or more homogeneously mixed hole transporting materials each having a glass transition temperature above 75 °C and which are structurally compatible.



↑
10

EP 0 774 883 A3



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 96 11 8022

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.6)
A	EP 0 650 955 A (HODOGAYA CHEMICAL CO LTD ;MATSUSHITA ELECTRIC IND CO LTD (JP)) 3 May 1995 * page 2, line 45 - page 11, line 50 * * page 65, line 23 - line 27 *	1-3	H05B33/14 H05B33/12
D,A	US 5 061 569 A (VANSLYKE STEVEN A ET AL) 29 October 1991 * column 7, line 17 - line 32 *	1-4	
A	EP 0 517 542 A (SUMITOMO CHEMICAL CO) 9 December 1992 * page 3, line 35 - page 4, line 54 * * page 13, line 46 - line 58 *	1-3	
A	EP 0 510 541 A (MITSUBISHI CHEM IND) 28 October 1992 * example 4 *	1-3	
D,A	US 5 256 945 A (IMAI KUNIO ET AL) 26 October 1993 * column 1, line 54 - column 2, line 20 * * column 3, line 40 - line 65 *	1-4	TECHNICAL FIELDS SEARCHED (Int.Cl.6) H05B
A	EP 0 611 148 A (SHIROTA YASUHIKO ;TDK CORP (JP)) 17 August 1994 * page 2, line 35 - page 5, line 28 * * figure 1 * * page 9, line 35 - line 37 *	1-4	
A	DATABASE WPI Section Ch, Week 9229 Derwent Publications Ltd., London, GB; Class L03, AN 92-238615 XP002032098 & JP 04 161 480 A (MITSUBISHI KASEI CORP) , 4 June 1992 * abstract *	1-3	
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 2 June 1997	Examiner Shade, M
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document			

EPO FORM 1503 (03/92) (P04C01)



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 96 11 8022

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.6)
A	WO 90 14744 A (EASTMAN KODAK CO) 29 November 1990 * page 21, line 20 - page 27, line 25 * * page 35, line 10 - line 14 *	1,2,5	
D,A	APPLIED PHYSICS LETTERS, vol. 66, no. 20, 15 May 1995, pages 2679-2681, XP000507576 ADACHI C ET AL: "MOLECULAR DESIGN OF HOLE TRANSPORT MATERIALS FOR OBTAINING HIGH DURABILITY IN ORGANIC ELECTROLUMINESCENT DIODES" * figures 1,4 *	1	
The present search report has been drawn up for all claims			TECHNICAL FIELDS SEARCHED (Int.Cl.6)
Place of search	Date of completion of the search	Examiner	
THE HAGUE	2 June 1997	Shade, M	
CATEGORY OF CITED DOCUMENTS		T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application I : document cited for other reasons & : member of the same patent family, corresponding document	
X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document			

EPO FORM 1503 01/92 (P04/C01)

THIS PAGE BLANK (USPTO)